

CREST REFINISHING SYSTEM

HIGH SOLIDS - CALIBER CLEARS

CALIBER ACTIVATORS

CALIBER 50



PERCENT SOLIDS
49 %.
HIGH QUALITY RESINS
EXCELLENT U.V. PROTECTION



2 : 1
MIX RATIO

RAPID CURE / HIGH SOLIDS
EURO PRODUCTION CLEAR
Stock #: BCC50

Stock #: BCCA60



FAST SPEED ACTIVATOR
60°F—70°F TEMP RANGE

FLASH TIME	4 - 8 min
DUST FREE	12 - 15 min.
SAND / BUFF	1.5 - 2 hours
DELIVER	3 hours

Stock #: BCCA70



MEDIUM SPEED ACT.
70°F—80°F TEMP RANGE

FLASH TIME	5 - 10 min
DUST FREE	15 - 20 min.
SAND / BUFF	2 - 3 hours
DELIVER	3 - 4 hours

Stock #: BCCA80 + 90



SLOW SPEED ACTIVATOR
80°F + 90 TEMP RANGE

FLASH TIME	10 - 15 min
DUST FREE	25 - 35 min.
SAND / BUFF	2 - 3 hours
DELIVER	3 - 4 hours

CALIBER 41

PERCENT SOLIDS
42 %.
HIGH QUALITY RESINS
EXCELLENT U.V. PROTECTION



4 : 1
MIX RATIO

HIGH SOLIDS \ HIGH GLOSS
OVERALL BAKE BOOTH CLEAR
Stock #: BCC

Stock #: BCCA60



FAST SPEED ACTIVATOR
60°F—70°F TEMP RANGE

FLASH TIME	10 - 15 min
DUST FREE	20 - 30 min.
SAND / BUFF	8 hours
DELIVER	16 + hours

Stock #: BCCA70



MEDIUM SPEED ACT.
70°F—80°F TEMP RANGE

FLASH TIME	10 - 15 min
DUST FREE	25 - 35 min.
SAND / BUFF	8 hours
DELIVER	16 + hours

Stock #: BCCA80 + 90



SLOW SPEED ACTIVATOR
80°F + 90 TEMP RANGE

FLASH TIME	10 - 15 min
DUST FREE	35 - 45 min.
SAND / BUFF	8 hours
DELIVER	16 + hours

HEAT CURING - Allow last coat to flash **10 - 15** minutes, then bake at **140°F / 60°C** for **30** minutes, Allow **one hour** to cool down before buffing.

CALIBER 38 Special

PERCENT SOLIDS
39 %.
HIGH QUALITY RESINS
EXCELLENT U.V. PROTECTION



4 : 1
MIX RATIO

O.E.M. APPEARANCE PRODUCTION
COLLISION CLEAR
Stock #: BCC38

Stock #: BCCA60



FAST SPEED ACTIVATOR
60°F—70°F TEMP RANGE

FLASH TIME	5 - 10 min
DUST FREE	10 - 15 min.
SAND / BUFF	8 hours
DELIVER	12 + hour

Stock #: BCCA70



MEDIUM SPEED ACT.
70°F—80°F TEMP RANGE

FLASH TIME	10 - 15 min
DUST FREE	15 - 20 min.
SAND / BUFF	8 hours
DELIVER	12 + hours

Stock #: BCCA80 + 90



SLOW SPEED ACTIVATOR
80°F + 90 TEMP RANGE

FLASH TIME	15 - 20 min
DUST FREE	20 - 25 min.
SAND / BUFF	8 hours
DELIVER	12 + hours

CALIBER LINE 9MM

PERCENT SOLIDS
37 %.
HIGH QUALITY RESINS
EXCELLENT U.V. PROTECTION



4 : 1
MIX RATIO

UNIVERSAL HIGH VOLUME
PRODUCTION CLEAR
Stock #: BCC9MM

Stock #: BCCA60



FAST SPEED ACTIVATOR
60°F—70°F TEMP RANGE

FLASH TIME	5 - 10 min
DUST FREE	10 - 15 min.
SAND / BUFF	8 hours
DELIVER	12+ hour

Stock #: BCCA70



MEDIUM SPEED ACT.
70°F—80°F TEMP RANGE

FLASH TIME	10 - 15 min
DUST FREE	15 - 20 min.
SAND / BUFF	8 hours
DELIVER	12+ hours

Stock #: BCCA80 + 90



SLOW SPEED ACTIVATOR
80°F + 90 TEMP RANGE

FLASH TIME	15 - 20 min
DUST FREE	20 - 25 min.
SAND / BUFF	8 hours
DELIVER	12 + hours



To see our Online Catalog visit:
To Order Call us toll free at:

www.CRESTEASTCOAST.com
866-458-9009



Credit Cards Accepted!

